



Optically Ultra High Clarity Polyester Film

(One side acrylic coating & other side untreated film)

SUPET S-105

Product Description

S-105 grade is a Bi axially Oriented **Ultra High Clarity** Polyester film with one side acrylic coated & other side Untreated film. This film is characterized by ultra high transparency & clarity.

Product features


- ❖ Very high clarity and transparency & gloss
- ❖ Excellent thermal & mechanical properties
- ❖ The coated side provide excellent ink adhesion
- ❖ Excellent processability.

Product Applications

- ❖ Suitable for holographic, metallization, lamination
- ❖ Labels, Photosensitive coatings, Glitter,

Food Contact

This film complies with US FDA, EC directive & REACH regulation for food packaging.



Head Office : 6/121 A-1, Paiki, Plot no.8, First floor,Vairagini wadi,Delhi gate Surat-395003,Gujarat , INDIA
TEL. NO: +91-261– 2441122 / 6797979, FAX NO: +91-261-2442952 , **web: www.sumilon.com**

WORKS: 43/P NH-8A, Village Varsana, Talq. Anjar, Gandhidham-370201, Gujarat (India). Phone No.: +91-2836-324900





Optically Ultra High Clarity Polyester Film

(One side acrylic coating & other side untreated film)

SUPET S-105

Technical Specification

Properties		Unit	Test Method	Typical Values				
General Properties								
Thickness		Micron Gauge	SITM	10 40	12 48	19 76	23 92	36 144
Yield		m²/kg	SITM	71	59	38	31	20
Grammage		gm/m²	SITM	14.0	16.8	26.6	32.2	50.4
Density		gm/cm³	SITM	1.4	1.4	1.4	1.4	1.4
Mechanical Properties								
Tensile Strength (Min)	MD	Kg/cm² Kpsi	ASTM D 882	2100 30	2100 30	2100 30	2100 30	1900 27
	TD			2000 28	2000 28	2000 28	2000 28	1900 27
Elongation at Break (Min)	MD	%	ASTM D 882	90	90	90	110	110
	TD			90	90	90	100	100
Surface Properties								
Coefficient of Friction (Max)	St.	-	ASTM D 1894	0.50	0.50	0.50	0.50	0.50
	Dy.			0.45	0.45	0.45	0.45	0.45
Wetting Tension on coated side		Dynes/cm	ASTM D 2578	38	38	38	38	38
Optical Properties								
Haze (Max)		%	ASTM D 1003	1.0	1.0	1.0	1.0	1.0
Transmittance(Min)		%	ASTM D 1003	90	90	90	90	90
Thermal Properties								
Heat Shrinkage @150°C/30minute (Max)	MD	%	ASTM D 1204	2.4	2.4	2.4	2.4	2.4
	TD			0.4	0.4	0.4	0.4	0.4
Barrier Properties								
WVTR(38°C& 90%RH)		gm/m²/day gm/100in²/d	ASTM F 1249	<65 <4.2	<40 <2.6	<30 <1.9	<25 <1.6	<22 <1.4
OTR (23°C & 0 %RH)		cc/m²/day cc/100in²/d	ASTM D3985	<145 <9.4	<135 <8.7	<100 <6.5	<75 <4.8	<55 <3.5

MD: Machine direction **TD:** Transverse direction **SITM:** Saj Industries Test Method.

The inherent surface tension on untreated side is min 42 dynes/cm.

Head Office : 6/121 A-1, Paiki, Plot no.8, First floor,Vairagini wadi,Delhi gate Surat-395003,Gujarat , INDIA
TEL. NO: +91-261- 2441122 / 6797979, FAX NO: +91-261-2442952 , **web: www.sumilon.com**

WORKS: 43/P NH-8A, Village Varsana, Talq. Anjar, Gandhidham-370201, Gujarat (India). Phone No.: +91-2836-324900





Optically Ultra High Clarity Polyester Film

(One side acrylic coating & other side untreated film)

SUPET S-105

Storage & Handling

Rolls are covered by stretch wrap and which may have the chances to attract the dust particles. Use SUPET film on FIFO system and advised to rotate the film stock. The storage hall should be away from flame/ heated substances. Also rolls kept away from the bad weather conditions. The recommended temperature is below 35°C with relative humidity of 55-60%. It is recommended that the film should not get exposed to direct Sunlight and water /moisture. This film is suitable for use one year from the date of manufacturing if store in recommended storage condition, afterward Sumilon will not accept any responsibility.

Disposal

Disposal of S-105 does not present special disposal problems. Where waste occurs in a clean, uncontaminated form, it can be recycled. In most circumstances, once S-105 has been laminated, coated, printed or metallized, incineration with Energy Recovery is the most environmentally efficient recovery route. It can also be burned in an incinerator with normal refuse. The disposal method should comply with appropriate local and country.

Disclaimer

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. Saj Industries Pvt. Ltd. suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.

TDS issued on 05.04.2023. All previous version of this grade are invalid.

Head Office : 6/121 A-1, Paiki, Plot no.8, First floor,Vairagini wadi,Delhi gate Surat-395003,Gujarat , INDIA
TEL. NO: +91-261– 2441122 / 6797979, FAX NO: +91-261-2442952 , **web: www.sumilon.com**

WORKS: 43/P NH-8A, Village Varsana, Talq. Anjar, Gandhidham-370201, Gujarat (India). Phone No.: +91-2836-324900

ISO 9001:2015
BUREAU VERITAS
Certification

