Easy Stackable Polyester Film

(One side high friction surface & other side Chemical coated film)

SUPET S-108A

Product Description

S-108A grade is a Bi axially Oriented Transparent Polyester film with one side modified high friction surface suitable for stacking the bulk pack & other side Chemical coated provide excellent adhesion with ink and adhesive.

Product features

- Modified surface with high friction properties
- Prevent slippage to improve stacking properties
- Excellent surface for printing & lamination
- Smooth run ability and winding with high friction side to chemical coated side on machine

Product Applications

- Stackable bulk packaging for bags, pouches

Food Contact

This film complies with US FDA, EC directive & REACH regulation for food packaging.



Head Office : 6/121 A-1, Paiki, Plot no.8, First floor,Vairagini wadi,Delhi gate Surat-395003,Gujarat , INDIA
TEL. NO: +91-261– 2441122 / 6797979, FAX NO: +91-261-2442952 , **web: www.sumilon.com**

WORKS: 43/P NH-8A, Village Varsana, Talq. Anjar, Gandhidham-370201, Gujarat (India). Phone No.: +91-2836-324900

ISO 9001:2015 BUREAU VERITAS Certification

Easy Stackable Polyester Film

(One side high friction surface & other side Chemical coated film)

SUPET S-108A

Technical Specification

Properties		Unit	Test Method	Typical Values	
General Properties					
Thickness		Micron Gauge	SITM	**12** **48**	**23** **92**
Yield		m^2/kg	SITM	59	31
Grammage		gm/m^2	SITM	16.8	32.2
Density		gm/cm^3	SITM	1.4	1.4
Mechanical Properties					
Tensile Strength (Min)	MD	Kg/cm^2 Kpsi	ASTM D 882	2100 30	2100 30
	TD			2000 28	2000 28
Elongation at Break (Min)	MD	%	ASTM D 882	90	110
	TD			90	100
Surface Properties					
Coefficient of Friction (High friction to high friction)	St.	-	ASTM D 1894	Block	Block
	Dy.			Block	Block
Wetting Tension on chemical coated side		Dynes/cm	ASTM D 2578	54+	54+
Optical Properties					
Haze (Max)		%	ASTM D 1003	3.5	4.0
Transmittance(Min)		%	ASTM D 1003	88	88
Thermal Properties					
Heat Shrinkage @150°C/30minute (Max)	MD	%	ASTM D 1204	2.4	2.4
	TD			0.4	0.4
Barrier Properties					
WVTR(38°C& 90%RH)		$gm/m^2/day$ $gm/100in^2/d$	ASTM F 1249	<45 <2.9	<25 <1.6
OTR (23°C & 0 %RH)		$cc/m^2/day$ $cc/100in^2/d$	ASTM D3985	<135 <8.7	<75 <4.8

MD: Machine direction **TD:** Transverse direction **SITM:** Saj Industries Test Method.

Head Office : 6/121 A-1, Paiki, Plot no.8, First floor,Vairagini wadi,Delhi gate Surat-395003,Gujarat , INDIA
TEL. NO: +91-261– 2441122 / 6797979, FAX NO: +91-261-2442952 , **web: www.sumilon.com**

WORKS: 43/P NH-8A, Village Varsana, Talq. Anjar, Gandhidham-370201, Gujarat (India). Phone No.: +91-2836-324900

ISO 9001:2015 BUREAU VERITAS Certification

Storage & Handling

Rolls are covered by stretch wrap and which may have the chances to attract the dust particles. Use SUPET film on FIFO system and advised to rotate the film stock. The storage hall should be away from flame/ heated substances. Also rolls kept away from the bad weather conditions. The recommended temperature is below 35°C with relative humidity of 55-60%. It is recommended that the film should not get exposed to direct Sunlight and water /moisture. This film is suitable for use one year from the date of manufacturing if store in recommended storage condition, afterward Sumilon will not accept any responsibility.

Disposal

Disposal of S-108A does not present special disposal problems. Where waste occurs in a clean, uncontaminated form, it can be recycled. In most circumstances, once S-108A has been laminated, coated, printed or metallized, incineration with Energy Recovery is the most environmentally efficient recovery route. It can also be burned in an incinerator with normal refuse. The disposal method should comply with appropriate local and country.

Disclaimer

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. Saj Industries Pvt. Ltd. suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.

TDS issued on 05.04.2023. All previous version of this grade are invalid.

Head Office : 6/121 A-1, Paiki, Plot no.8, First floor,Vairagini wadi,Delhi gate Surat-395003,Gujarat , INDIA
TEL. NO: +91-261– 2441122 / 6797979, FAX NO: +91-261-2442952 , **web: www.sumilon.com**

WORKS: 43/P NH-8A, Village Varsana, Talq. Anjar, Gandhidham-370201, Gujarat (India). Phone No.: +91-2836-324900

ISO 9001:2015
BUREAU VERITAS
Certification