Dead Fold Retainable Grade Polyester Film

(Both side untreated film)

SUPET S-550

Product Description

S-550 grade is a Bi axially oriented dead fold retainable grade polyester film with no surface treatment. This film is ideal for twist wrap packaging for confectionery. This film is specially designed for high dead fold retention.

Product features

- Excellent fold retention properties
- Excellent Optical & thermal properties
- Excellent mechanical properties
- Excellent process ability

Product Applications

- Candy ,toffees wrapping (Hot & Cold)
- Printing, Metalizing and Lamination

Food Contact

This film complies with US FDA , EC directive & REACH regulation for food packaging.



Head Office : 6/121 A-1, Paiki, Plot no.8, First floor,Vairagini wadi,Delhi gate Surat-395003,Gujarat , INDIA
TEL. NO: +91-261– 2441122 / 6797979, FAX NO: +91-261-2442952 , **web: www.sumilon.com**

WORKS: 43/P NH-8A, Village Varsana, Talq. Anjar, Gandhidham-370201, Gujarat (India). Phone No.: +91-2836-324900

ISO 9001:2015
BUREAU VERITAS
Certification

Dead Fold Retainable Grade Polyester Film

(Both side untreated film)

SUPET S-550

Technical Specification

Properties		Unit	Test Method	Typical Values			
General Properties							
Thickness		Micron Gauge	SITM	**12** **48**	**15** **60**	**18** **72**	**23** **92**
Yield		m^2/kg	SITM	59	48	40	31
Grammage		gm/m^2	SITM	16.8	21.0	25.2	32.2
Density		gm/cm^3	SITM	1.4	1.4	1.4	1.4
Mechanical Properties							
Tensile Strength (Min)	MD	Kg/cm^2 Kpsi	ASTM D 882	2200 31	2200 31	2200 31	2100 30
	TD			2200 31	2200 31	2200 31	2100 30
Elongation at Break (Min)	MD	%	ASTM D 882	100	100	90	90
	TD			80	80	80	80
Surface Properties							
Coefficient of Friction (Max)	St.	-	ASTM D 1894	0.50	0.50	0.50	0.50
	Dy.			0.45	0.45	0.45	0.45
Wetting Tension on untreated side		Dynes/cm	ASTM D 2578	42	42	42	42
Optical Properties							
Haze (Max)		%	ASTM D 1003	3.5	3.5	3.5	4.0
Transmittance(Min)		%	ASTM D 1003	88	88	88	88
Thermal Properties							
Heat Shrinkage @150^{0}C/30minute (Min)	MD	%	ASTM D 1204	25	25	25	25
	TD			25	25	25	25
Barrier Properties							
WVTR(38°C& 90%RH)		$gm/m^2/d$ $gm/100in^2/d$	ASTM F 1249	<40 <2.6	<35 <2.3	<30 <1.9	<25 <1.6
OTR (23°C & 0 %RH)		$cc/m^2/day$ $cc/100in^2/d$	ASTM D3985	<135 <8.7	<120 <7.7	<100 <6.4	<75 <4.8

MD: Machine direction **TD:** Transverse direction **SITM:** Saj Industries Test Method.

Head Office : 6/121 A-1, Paiki, Plot no.8, First floor,Vairagini wadi,Delhi gate Surat-395003,Gujarat , INDIA
TEL. NO: +91-261– 2441122 / 6797979, FAX NO: +91-261-2442952 , **web: www.sumilon.com**

WORKS: 43/P NH-8A, Village Varsana, Talq. Anjar, Gandhidham-370201, Gujarat (India). Phone No.: +91-2836-324900

ISO 9001:2015
BUREAU VERITAS
Certification

Storage & Handling

Rolls are covered by stretch wrap and which may have the chances to attract the dust particles. Use SUPET film on FIFO system and advised to rotate the film stock. The storage hall should be away from flame/ heated substances. Also rolls kept away from the bad weather conditions. The recommended temperature is below 35°C with relative humidity of 55-60%. It is recommended that the film should not get exposed to direct Sunlight and water /moisture. This film is suitable for use one year from the date of manufacturing if store in recommended storage condition, afterward Sumilon will not accept any responsibility.

Disposal

Disposal of S-550 does not present special disposal problems. Where waste occurs in a clean, uncontaminated form, it can be recycled. In most circumstances, once S-550 has been laminated, coated, printed or metallized, incineration with Energy Recovery is the most environmentally efficient recovery route. It can also be burned in an incinerator with normal refuse. The disposal method should comply with appropriate local and country.

Disclaimer

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. Saj Industries Pvt. Ltd. suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.

TDS issued on 05.04.2023. All previous version of this grade are invalid.

Head Office : 6/121 A-1, Paiki, Plot no.8, First floor,Vairagini wadi,Delhi gate Surat-395003,Gujarat , INDIA
TEL. NO: +91-261– 2441122 / 6797979, FAX NO: +91-261-2442952 , **web: www.sumilon.com**

WORKS: 43/P NH-8A, Village Varsana, Talq. Anjar, Gandhidham-370201, Gujarat (India). Phone No.: +91-2836-324900

ISO 9001:2015
BUREAU VERITAS
Certification